



PAINT SPRAY BOOTH COATING PRODUCT SPECIFICATIONS

Product Name: 791-WH White Solvent-Based Peelable Booth Coating
Product Code: 791-WH

Intended Use: This product was designed as a peelable spray booth coating intended to make clean up of paint overspray quick and easy.

Special Properties:

1. White film for better booth illumination.
2. Fast Dry time
3. Forms a tough flexible film that is easily peeled.
4. Dry film is non-flammable.

Typical Properties:

Color: White
Viscosity: 70 +/- 5 Krebs units
Solids by Weight: 30 +/- 5%
Solids by Volume: 26 +/- 3%
Density: 7.5 +/- 0.5 lbs. per gallon
V.O.C. (theoretic): 5.0 lbs. per gallon
Coverage (average): 200-225 sq. ft. per gallon @ 2.0 dry mil

Application Data:

Method: Apply by pressurized spray.
Reduction: Apply as supplied. If a reduction is needed, acetone or any strong lacquer thinner may be used.
Substrate: Spray on clean, smooth steel
Cure: Air dry 30 minutes

Recommended Dry Film Thickness: Apply 2-3 dry mils
Recommended Wet Film Thickness: Apply 6-8 wet mils
Clean Up: Use ketone solvents or any strong lacquer thinner.
Storage: If chilled below 30 degrees Fahrenheit 791 may form a gel-like consistency. Warm the contents of the container to 65-70 degrees Fahrenheit and agitate to return the material to application condition.
Shelf Life: 12 months.

This product is not designed for applications that are subject to periods of elevated temperatures or exposure to sunlight. **THIS PRODUCT IS NOT RECOMMENDED FOR USE IN SPRAYBOOTH BAKE OVENS.**

This product is recommended for application to many different types of surfaces. These surfaces include steel, galvanized steel, aluminum, and diecast. Chemco recommends that all surfaces be cleaned prior to use.

Chemco recommends testing prior to use on any other type of surface.

For any questions regarding this product, please call 800-323-0431, fax 800-336-7706, email @ nbinfo@chemcomfg.com